

# INTERNATIONAL CENTRE FOR AUTOMOTIVE TECHNOLOGY

[A Division of NATRIP Implementation Society (NATIS), Govt. of India]

Non-Transferable

## TEST REPORT

Test Report No.: **CT0BN5180**

Date: **12.06.2018**

- 1.0 **NAME AND ADDRESS OF THE CUSTOMER:** M/s Eastman Auto & Power Limited  
Khasra No. 315/252/1-4 Nalagarh Pinjore Highway  
Nalagarh District Solan (H.P.) 174101, India
- 1.1 **NAME AND ADDRESS OF THE MANUFACTURER:** Same as Sr. No. 1.0
- 2.0 **CUSTOMER LETTER REF :** IOCS No. CCTNEAPLNDEEG59270 Dated 09-Apr-2018

3.0 **DESCRIPTION OF DEVICE UNDER TEST (DUT):**

DUT Name : Battery Module, 12 V  
 Battery Type : Lead Acid Battery  
 Battery Capacity(Ah) : 75Ah (Ah in 5 hrs)  
 Rated Voltage : 12 Volt DC  
 Id/Model No. : EM1009ER  
 Quantity : 06 Nos.  
 (ICAT/AEEL/59270/01-06)

Trade Name : Eastman  
 Drawing No. : EAP-ER-40-0411(C-115)

- 4.0 **DATE OF RECEIPT OF SAMPLE :** 27.04.2018
- 5.0 **CONDITION OF SAMPLE :** No Physical Damage observed
- 6.0 **TEST OBJECTIVE:**


To validate the Safety Requirements of Traction Batteries as per AIS: 048 amended up to date


- 7.0 **TEST METHOD:** Test method referred from AIS: 048 as amended up to date.
- 8.0 **FUNCTIONAL VERIFICATION:** Functional verification done and battery was found satisfactory
- 9.0 **CONCLUSION:**

The battery specified in Sr. No. 3.0 of this test report met all the test requirements when tested as per AIS: 048 amended up to date as mentioned in Annexure No. 1 of this report.

- 10.0 **TEST DISCRIPTION:** Please refer the Annexure No. 1 of this report.
- 11.0 **DATE OF PERFORMANCE OF TEST:** Please refer the Annexure No. 1 of this report.
- 12.0 **TEST RESULTS:**

Please refer the Test requirements and Results in Annexure-I of this report.



Prepared By	Checked By		Approved By	
				 BN5180  Page 1 of 7 + Dwg (01) [59270]
<b>UDIT KAUL</b> Asst. Manager	<b>MAHENDAR PAL</b> Sr. Manager		<b>PAMELA TIKKU</b> Sr. General Manager	

Innovation • Service • Excellence

Test Report No.: C T 0 B N 5 1 8 0

Date: 12.06.2018

**DISCLAIMER**

1. ICAT issues Test reports/ Extension reports/ Developmental Reports for vehicles/ parts/ components/ assemblies etc. based on the documents produced and/or prototype / vehicle(s) or sample(s) submitted by the applicant and testing thereof.
2. ICAT issues Test reports/ Extension reports/ Developmental Reports in compliance to Motor Vehicle Act/ Central Motor Vehicle Rules and their provisions as amended from time to time or any other statutory orders under which ICAT is authorized. Other Rules/Acts are outside the purview/scope of the Test reports/Extension reports/ Developmental test reports
3. Test(s) on prototype/ vehicle(s)/ sample(s) is/are carried out on the basis of standard procedures as notified under specific rules/ requested by the applicant. Results of such tests are property of bearer of Test Reports/ Extension Reports / Developmental test reports. These results cannot be disclosed unless specifically so ordered by Government, Court, etc
4. Unless otherwise supported by a separate Certificate, this Test report Extension Reports / Developmental test reports shall not be considered in isolation as valid Type approval for any vehicle
5. ICAT is not responsible for testing each vehicles/ parts/assemblies etc. for which Test Reports/ Extension reports/ Developmental test reports is issued. Further, ICAT is not responsible for ensuring manufacturing quality of the vehicles/ components/ parts/ assemblies etc. for which the Test Reports/ Extension reports/ Developmental test reports is /are issued.
6. ICAT is no way responsible for any misuse or copying any design/type/system in connection with entire vehicle/ components/parts and assemblies covered under the Test Reports/ Extension reports/ Developmental test reports is /are issued
7. Breach of any statutory provisions, of Indian laws or laws of other countries, will be sole responsibility of the customer. ICAT shall not be liable for any claims or damages made by the customer, whatsoever. The customer shall alone be liable for the same and undertakes to indemnify ICAT in this regard
8. Further, ICAT has the right, but not under obligation to initiate cancellation / withdrawal of the Test report/Extension/ Developmental test report is/are issued, in case of any fraud, misrepresentation, when it surfaces and comes in the knowledge of ICAT
9. No extract, abridgment or abstraction from this test report may be published or used to advertise the product without the written consent of the Director, ICAT, who reserves the absolute right to agree or reject all or any of the details of any items of publicity for which consent may be sought
10. The appropriate local court at Gurgaon shall have the jurisdiction in respect of any dispute, claim or liability arising out of this report.

Innovation • Service • Excellence


Prepared By		Checked By	Page 2 of 7 + Dwg (01) [59270]
			
<b>UDIT KAUL</b> Asst. Manager		<b>MAHENDAR PAL</b> Sr. Manager	

Test Report No.: C T 0 B N 5 1 8 0

Date: 12.06.2018

Annexure – I


1.0 TEST REQUIREMENTS AND RESULTS:

Cl. No.	Test	Test Description	Observations/Results
<b>2.1 Electrical Tests</b>			
2.1.1	<p><b>Short Circuit test</b> (Test ID:ICAT/AEEL/59270/01) Date of Test : 07.05.2018</p>	 <p>Battery Condition: Fully charged (100% SOC), contained at ambient temperature. Apply a hard short in less than one second to the battery module with a conductor specified in the standard. Test Duration: 10 minutes, or until another condition occurs which prevents completion of test (i.e. component melting, etc.) Lab temperature: Not exceeding 30°C</p> <p><b>Acceptance Criteria:</b> After 2 hours of observation: At the end of the test, there shall be no: a) Physical damage to the casing or mechanical parts. b) Melting of components. c) Fire or explosion. It is acceptable for the battery to become dry at the end of the test.</p>	<p>Ambient temperature : 27°C</p> <p>Conductor of <math>\leq 5m\Omega</math> was used and short was applied for 10 minutes.</p> <p>No physical damage, explosion or melting observed.</p> <p><b>Satisfactory.</b></p>

<p><b>Prepared By</b></p>  <p><b>UDIT KAUL</b> Asst. Manager</p>		<p><b>Checked By</b></p>  <p><b>MAHENDAR PAL</b> Sr. Manager</p>
<p>Page 3 of 7 + Dwg (01) [59270]</p>		

Test Report No.: C T 0 B N 5 1 8 0

Date: 12.06.2018

<p>2.1.2</p>	<p><b>Over Charge test</b> (Test ID: ICAT/AEEL/59270/02) Date of Test : 07.05.2018</p>	 <p>Battery Condition: Fully charged (100% SOC), contained at ambient temperature at 27±5°C. Duration: 10 hours The battery is to be overcharged at a constant charging current of 0.1 (C<sub>10</sub>). <b>Acceptance Criteria:</b> At the end of the test, there shall be no: a) Physical damage to the casing or other mechanical parts. b) Melting of components. c) Fire or explosion.</p>	<p>Battery Module was charged with 8.33 A for 10 hours.</p> <p>No physical damage, melting or explosion observed.</p> <p><b>Satisfactory.</b></p>
--------------	--	---	---



<p>Prepared By</p> 		<p>Checked By</p> 	<p>Page 4 of 7 + Dwg (01) [59270]</p>
<p><b>UDIT KAUL</b> Asst. Manager</p>		<p><b>MAHENDAR PAL</b> Sr. Manager</p>	


2.2 Mechanical Tests

2.2.1	<p><b>Vibration test</b> (Test ID: ICAT/AEEL/59270/03) Date of test : 06.06.2018</p>	 <p>Battery Condition: Fully charged (100% SOC), contained at ambient temperature, firmly held on the vibration table in vehicle mounting position. Axis: Vertical and Horizontal axis, with battery positioned in longitudinal direction. Acceleration: 3 g (sinusoidal vibration) Frequency: 30-150 Hz Sweep rate: 1 octave per minute Duration: 2 hours in each axis Immediately after the test, discharge the battery at room temperature not exceeding 30°C, at the rate of <math>I = 0.2 \times \text{Battery capacity}(C_5)</math></p> <p><b>Acceptance Criteria:</b> During test, there shall be no electrolyte loss. The deterioration of battery rated capacity during discharging shall not be more than 10%. At the end of the test, there shall be no: a) Physical damage to the casing or other mechanical parts b) Fire or explosion</p>	<p>No electrolyte loss observed during test.</p> <p>Immediately after the test, battery was discharged at 15 A And deterioration observed was not more than 10%.</p> <p>No physical damage or explosion observed.</p> <p><b>Satisfactory.</b></p>
-------	--	--	---

Prepared By		Checked By	
			
UDIT KAUL Asst. Manager		MAHENDAR PAL Sr. Manager	Page 5 of 7 + Dwg (01) [59270]

Test Report No.: CT0BN5180


Date: 12.06.2018

<p>2.2.2</p>	<p><b>Shock test</b> (Test ID: ICAT/AEEL/59270/04) Date of test : 08.05.2018</p>	  <p>Battery Condition: Fully charged (100% SOC), contained at ambient temperature not exceeding 30°C, firmly held on the vibration table in vehicle mounting position. Axis: Vertical and Horizontal axis, with battery positioned in longitudinal direction. Acceleration: 30 g (half-sine wave) No. of shocks: 10 in each axis Duration: 15 ms of each shock Immediately after the test, discharge the battery at room temperature, at the rate of <math>I = 0.2 \times \text{Battery capacity}(C_5)</math> <b>Acceptance Criteria:</b> The deterioration of battery rated capacity during discharging shall not be more than 10%. At the end of the test, there shall be no: a) Physical damage to the casing or other mechanical parts b) Fire or explosion.</p>	<p>Immediately after the test, battery was discharged at 15 A and deterioration observed was not more than 10%.</p> <p>No physical damage or explosion observed.</p> <p><b>Satisfactory.</b></p>
--------------	--	---	--

<p>Prepared By</p>  <p><b>UDIT KAUL</b> Asst. Manager</p>		<p>Checked By</p>  <p><b>MAHENDAR PAL</b> Sr. Manager</p>	<p>Page 6 of 7 + Dwg (01) [59270]</p>
--	---	---	---

Test Report No.: C T 0 B N 5 1 8 0

Date: 12.06.2018

<p>2.2.3</p>	<p><b>Roll-Over Test</b> (Test ID: ICAT/AEEL/59270/05) Date of test : 07.05.2018</p>	 <p>Rotate the battery module one complete revolution in one direction, for one minute in a continuous, slow-roll fashion, and observe leakage, if any. Then rotate the battery module in 90° increments in same direction for one full revolution. Hold the battery module for one hour at each position. <b>Acceptance Criteria:</b> The volume of electrolyte spilled in each position shall not be more than 25 ml per module.</p>	<p>Spillage observed was less than 25ml in each position.  <b>Satisfactory.</b></p>
<p>2.2.4</p>	<p><b>Penetration Test</b> (Test ID: ICAT/AEEL/59270/06) Date of test : 16.05.2018</p>	 <p>The battery shall be penetrated with a mild steel (conductive) pointed rod, which will be electrically insulated from the test fixture. Rate of penetration: <b>8 cm/s.</b> Diameter of Rod: <b>20mm</b> Orientation of penetration: <b>perpendicular to the electrode plates.</b> Minimum Depth of penetration: <b>Through three cells or 100 mm.</b> The battery should be observed, with the rod remaining in place, for a minimum of one hour after the test. <b>Acceptance Criteria:</b> At the end of the test, there shall be no: a) Melting of components. b) Fire or explosion.</p>	<p>After penetration, up to a depth of 100 mm with a pointed mild steel rod of diameter 20mm, electrically insulated from the test fixture, no explosion, no fire and no melting observed.  <b>Satisfactory.</b></p>


<p>Prepared By</p> 		<p>Checked By</p> 	<p>Page 7 of 7 + Dwg (01) [59270]</p>
<p><b>UDIT KAUL</b> Asst. Manager</p>		<p><b>MAHENDAR PAL</b> Sr. Manager</p>	

Test Report No. :-> CT0BN5180





dated :- 12.06.2018

This drawing is the sole property of M/S Eastman Auto & Power Ltd. and issued on the condition that no further disclosure is made without written permission from M/S Eastman Auto & Power Ltd.

Over all Length =  $411 \pm 3$ mm



Engrave Assembly Code here



REV. NO.	REV. BY	DATE	REV. BY	CD. BY	APD. BY
A					

2018 NAME	SYGN. DATE	REV. BY	DATE	CD. BY	APD. BY
Eastman	30/02				Eastman Auto & Power Ltd. NALAGARH (HP - INDIA)
DRN. BY	30/02				...Let's grow together
CD. BY	30/02				MODEL : EM1009ER
APD. BY	30/02				DRG. NO. : EAP-ER-0-0411(C-115)

GENERAL TOLERANCE (mm)	UNLESS OTHERWISE SPECIFIED
BEYOND ( > )	0.5
BELOW ( < )	0.1
1	0.1
6	0.2
30	0.3
80	0.5
300	0.8
600	0.8

MATERIAL:	FINISH:
UNLESS OTHERWISE SPECIFIED	Smooth
TOLERANCE = REF. TO CHART	
Rev. 01	